

Materiály – Dvouvrstvé

	ISOLA – DE104					ISOLA – IS400					ISOLA – PCL370HR				
	Tg [°C]	T288 [min]	Td [°C]	CTEz (pre-Tg/post-Tg)	CTI třída (V)	Tg [°C]	T288 [min]	Td [°C]	CTEz (pre-Tg/post-Tg)	CTI třída (V)	Tg [°C]	T288 [min]	Td [°C]	CTEz (pre-Tg/post-Tg)	CTI třída (V)
	135	12(T260)	315	70/250	2 (250–399)	150	10	330	50/260	3 (175–249)	180	30	340	45/230	3 (175–249)
	datasheet					daasheet					datasheet				
tloušťka materiálu (μm)	tloušťka Cu (μm)					tloušťka Cu (μm)					tloušťka Cu (μm)				
	18/18	35/35	70/70	105/105	140/140	18/18	35/35	70/70	105/105	140/140	18/18	35/35	70/70	105/105	140/140
500	✓	○	○	○	○	○	○	○	○	○	○	○	○	○	○
800	✓	✓	○	○	○	○	○	○	○	○	○	○	○	○	○
1000	✓	✓	✓	○	○	✓	○	○	○	○	○	○	○	○	○
1200	✓	✓	○	○	○	○	○	○	○	○	○	○	○	○	○
1500	✓	✓	✓	✓	○	✓	✓	✓	○	○	✓	○	✓	○	○
2000	✓	✓	✓	○	○	✓	○	○	○	○	○	○	○	○	○
2400	✓	✓	○	○	○	○	○	○	○	○	○	○	✓	○	○
3200	✓	○	○	○	○	○	○	○	○	○	○	○	○	○	○

✓ skladem ○ na objednání